

AURELIA® TRANSFORM

3.2mil, Nitrile Powder Free Examination Gloves

Quality Ice Blue Nitrile examination gloves that offer increased tensile strength and protection over Latex and Vinyl.



Thin Nitrile examination gloves specifically designed to offer increased comfort, flexibility & sensitivity.
3.2mil Powder-Free Nitrile
Non-Sterile
Beaded cuff
Ambidextrous
Latex Free
AQL 1.5



Regulations	PPE Reugulation (EU) 2016/425 Medical Device Regulation (EU) 2017/745, 93/42/EEC
Quality Standards	ISO 9001:2015 Quality Management Systems. ISO 13485: 2016 Medical Devices Quality Management Systems.
Harmonised Standards	BS EN ISO 374 - 1 Protective gloves against dangerous chemicals, Type C BS EN ISO 374 - 5 Protective gloves against microorganisms (Virus). BS EN 455 1-4 Medical gloves for single use. EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1186:2002 Materials and articles in contact with foodstuffs.

AURELIA® GLOVES

M L XL
Codes:
TRANSFORM/M
TRANSFORM/L
TRANSFORM/XL

Sizes & Dimensions	Single Wall Thickness	Physical Properties													
 M 95±10 mm L 110±10 mm XL > 110 mm min. 240 mm min. 240 mm min. 240 mm	 ① min. 0.10mm ② min. 0.06mm ③ min. 0.05mm	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 14.0 MPa</td> <td>Min. 14.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 500%</td> <td>Min. 400%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 6N</td> <td>Min. 6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa	Elongation	Min. 500%	Min. 400%	Strength at Break	Min. 6N	Min. 6N	
	Unaged	Aged													
Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa													
Elongation	Min. 500%	Min. 400%													
Strength at Break	Min. 6N	Min. 6N													



Nitrile



Powder Free



5 Years



Finger Textured



3.6g +/- 0.2g



Ice Blue

